

# Repair and Remanufacture of Pipeline Valves

API RECOMMENDED PRACTICE 6DR  
FIRST EDITION, FEBRUARY 2006



Copyright American Petroleum Institute  
 Provided by IHS under license with API  
 No reproduction or networking permitted without license from IHS

Not for Resale

# Repair and Remanufacture of Pipeline Valves

**Upstream Segment**

API RECOMMENDED PRACTICE 6DR  
FIRST EDITION, FEBRUARY 2006



## SPECIAL NOTES

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

*All rights reserved. No part of this work may be reproduced, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, N.W., Washington, D.C. 20005.*

Copyright © 2006 American Petroleum Institute

## FOREWORD

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, N.W., Washington, D.C. 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually and updated quarterly by API, 1220 L Street, N.W., Washington, D.C. 20005.

Suggested revisions are invited and should be submitted to the Standards and Publications Department, API, 1220 L Street, NW, Washington, DC 20005, [standards@api.org](mailto:standards@api.org).

Copyright American Petroleum Institute  
Provided by IHS under license with API  
No reproduction or networking permitted without license from IHS

# CONTENTS

	Page
1 SCOPE.....	1
2 REFERENCED DOCUMENTS.....	1
3 TERMS AND DEFINITIONS .....	1
4 PREPARATION FOR SHIPMENT TO THE RECONDITIONER .....	2
5 CONTROL OF EQUIPMENT .....	2
6 DISASSEMBLY AND CLEANING OF VALVES .....	2
7 EVALUATION OF COMPONENTS .....	3
8 REPAIR/REMANUFACTURE/REPLACEMENT OF VALVE PARTS .....	3
8.1 Control of Manufacturing Operations.....	3
8.2 Inspection of Valve Parts .....	3
8.3 Replacement Parts and Material .....	3
8.4 Fabrication Welding.....	3
8.5 Repair Welding .....	3
8.6 Non-Destructive Examination (NDE).....	4
9 REASSEMBLY.....	4
10 FINAL ACCEPTANCE .....	4
10.1 Pressure Testing .....	4
10.2 Customer Notification .....	4
11 EQUIPMENT MARKING .....	4
11.1 Nameplates .....	4
11.2 Marking.....	4
12 PREPARATION FOR SHIPMENT AND SHORT TERM STORAGE.....	5
13 DOCUMENTATION .....	5
13.1 General Documentation .....	5
APPENDIX A MINIMUM REQUIREMENTS FOR EVALUATION AND RECONDITIONING OF PARTS .....	7
BIBLIOGRAPHY.....	9





# Repair and Remanufacture of Pipeline Valves

## 1 Scope

This Recommended Practice (RP) provides guidelines for the repair and remanufacture of steel ball, check, gate, and plug valves normally used in pipeline applications, as defined by API Spec 6D.

This RP covers repair or remanufacturing of end user's (owner's) valves for continued service in the owner's production applications. It does not cover repair or remanufacture of used or surplus valves intended for resale.

Repaired or remanufactured valves may not meet API and/or the OEM standard requirements for new valves.

The owner is responsible for the correct application of valves repaired or remanufactured per this document.

Field repair is outside the scope of this document.

## 2 Referenced documents

The following documents contain provisions which, through reference in this text, constitute provisions of this standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the documents listed below. For undated references, the latest edition of the document referred to applies. Referenced standards may be either the applicable edition shown herein or the latest revision, provided the reconditioner can show that the latest edition meets or exceeds requirements of the specific edition listed. When the latest edition is specified, it may be used on issue, and shall become mandatory six months from the date of the revision.

### API

Spec 6D      *Petroleum and Natural Gas Industries-Pipeline Transportation Systems-Pipeline Valves*

### ASME<sup>1</sup>

Section V      *Non-Destructive Evaluation*

Section IX      *Welding and Brazing Qualifications*

### ASTM<sup>2</sup>

A193      *Specification for Alloy Steel and Stainless Steel Bolting Materials for High Temperature Service*

A194      *Specification for Carbon and Alloy Steel Nuts for Bolts in High Pressure and High Temperature Service*

A320      *Specification for Alloy Steel Bolting Materials for Low Temperature Service*

### ASNT<sup>3</sup>

SNT-TC-1A      *Personnel qualification and certification in non-destructive testing*

### MSS<sup>4</sup>

MSS-SP-25      *Standard Marking System for Valves, Fittings, Flanges and Unions*

### NACE<sup>5</sup>

MR0175/ISO 15156      *Materials for use in H<sub>2</sub>S-containing environments in oil and gas production*

## 3 Terms and Definitions

For purposes of this document, the definitions in API Spec 6D along with the following definitions apply:

**3.1 end user, owner:** The entity that holds title to or applies the valve to a particular process.

<sup>1</sup>ASME International, 3 Park Avenue, New York, New York 10016-5990, [www.asme.org](http://www.asme.org)

<sup>2</sup>ASTM International, 100 Bar Harbor Drive, West Conshohocken, Pennsylvania 19428-2959, [www.astm.org](http://www.astm.org).

<sup>3</sup>American Society for Nondestructive Testing, Inc., 1711 Arlington Lane, P.O. Box 28518, Columbus, Ohio 43228-0518, [www.asnt.org](http://www.asnt.org).

<sup>4</sup>Manufacturers Standardization Society of the Valve and Fittings Industry, Inc., 127 Park Street, N.E., Vienna, Virginia 22180-4602, [www.mss.hq.com](http://www.mss.hq.com).

<sup>5</sup>NACE International (formerly the National Association of the Corrosion Engineers), 1440 South Creek Drive, P.O. Box 218340, Houston, Texas 77218-8340, [www.nace.org](http://www.nace.org).

**3.2 NORM:** Naturally Occurring Radioactive Material.

**3.3 OEM:** Original Equipment Manufacturer.

**3.4 recondition:** Repair and/or remanufacture.

**3.5 remanufacture:** Activities involving disassembly, reassembly, and testing with or without replacement of parts. Machining, welding, heat-treating, other manufacturing operations, or replacement of bodies may be employed.

**3.6 repair:** Activities involving disassembly, reassembly, and testing with or without replacement of parts. Repair does not include machining, welding, and heat-treating, other manufacturing operations, or replacement of bodies. Buffing, polishing, deburring, and other minimal removal processes are not considered machining and may be employed in repair processes.

## 4 Preparation for Shipment to the Reconditioner

The owner shall do the following before sending the equipment to the reconditioner:

- a. All pressure shall be removed from valves and accompanying actuators, tanks, etc.
- b. Hazardous materials shall be removed and cleaned from the valve and accompanying equipment.
- c. Valves should be checked for NORM in accordance with the applicable local regulations (region/state/country/province). Valves containing NORM may require special handling and cleaning procedures.

## 5 Control of Equipment

The valve shall be identified by the owner name/location or other appropriate identifier.

Each valve shall be assigned a unique identification number<sup>6</sup>. This number shall be traceable back to the pertinent instructions and or information provided by the owner.

A visual inspection shall be conducted to determine if the valve can be reconditioned. If valve cannot be reconditioned, notify the customer for disposition instructions.

Disposition may include one or more of the following:

- a. Salvage useable parts.
- b. Scrap in accordance with the owner's instructions.
- c. Return to the owner.

## 6 Disassembly and Cleaning of Valves

Valves to be reconditioned shall be completely disassembled. Packing, gaskets, and non-metallic parts shall be removed and disposed of in accordance with the owner's instructions and appropriate safety procedures.

The Original Equipment Manufacturer (OEM) tag shall not be removed. Damaged tags which cannot be properly attached shall be retained in the reconditioned valve document file. Tags from previous reconditioning shall be removed and the tag(s) or information from the tag(s) placed in the reconditioned valve document file. Tags may be electronically scanned or the information recorded and kept in the reconditioning document files.

The new identifier number shall be stamped on body, bonnet, cover, closure member, seats (if removed), stem and any other major components, using low stress stencils. If stamping is not practical, parts may be tagged or electro etched, except that all stems and closure elements for valves 2 in. and larger valves shall be marked by stamping. Identification numbers marked on parts shall remain on the parts throughout the reconditioning process. Smaller parts may be placed in a container labeled with the unique identification number.

Marking/labeling shall be of a type and material that resists damage, fading, or loss for a period of time consistent with the expected storage period.

Valve parts shall be cleaned using any of the usual cleaning methods. These include but are not limited to steam, chemical, sand/bead, or shot blasting. Finished surfaces that may be damaged shall be protected.

---

<sup>6</sup>May be alpha-numeric.

## 7 Evaluation of components

All components shall be inspected and evaluated in accordance with documented procedures. This shall consist of the following, as a minimum:

- Visual and dimensional inspection as to suitability for reuse.
- Verification of API Spec 6D specified flange and end-to-end dimensions.
- Evaluation as to valve fitness and function.

Appendix A provides minimum requirements for evaluation of components.

## 8 Repair/Remanufacture/Replacement of Valve Parts

### 8.1 CONTROL OF MANUFACTURING OPERATIONS

Repair and remanufacture operations shall be performed in accordance with documented procedures.

### 8.2 INSPECTION OF VALVE PARTS

Valve parts shall be inspected to determine their acceptability for re-use and/or extent of required repair. Inspection shall be performed per documented procedures not less stringent than the OEM or owner's requirements.

Equipment for measuring dimensions shall be controlled and calibrated in accordance with the reconditioner's methods specified in documented procedures which shall be consistent with nationally or internationally recognized standards.

### 8.3 REPLACEMENT PARTS AND MATERIAL

Source of replacement parts shall be one or more of the following:

- a. Suitable replacement parts from the OEM.
- b. Parts obtained from similar valves from the same valve manufacturer. The material must be identified, and critical dimensions verified to be the same as the original component.
- c. Manufactured or repaired component parts, from the recondition facility. These parts shall be made from materials equivalent to the original. Where the material cannot be determined or it is desirable to substitute a material different from the original, the part design shall be supported by the OEM's design file or the reconditioner's design file which is not less stringent than the OEM design file.

Replacement parts shall be made from materials that are procured to written specifications. Specifications for metallic parts shall, as a minimum, specify requirements for chemistry, heat treatment, mechanical properties, testing, and dimensions. Materials for replacement valve parts exposed to sour service shall comply with NACE MR0175/ISO 15156.

### 8.4 FABRICATION WELDING

Weld procedures used for pressure or load bearing fabrication welds in pressure containing and/or pressure-controlling parts shall be qualified in accordance with ASME Section IX or EN 288-3. Welders shall be qualified per ASME Section IX or EN 287-1.

Weld procedures used for pressure or load bearing welds in pressure containing and/or pressure-controlling parts for low temperature materials shall also be qualified in accordance with the applicable sections of the current edition of API Spec 6D/ISO 14313 relating to Impact Testing of welds.

Procedures for non-pressure retaining or non-load bearing welds shall be qualified per the reconditioner's requirements. Weld Procedure Specifications (WPS) shall be documented, qualified, and a copy of the Procedure Qualification Record (PQR) retained.

All weld procedures used for wetted components in valves intended for use in sour oil or gas shall also meet the requirements of NACE MR0175/ISO 15156.

### 8.5 REPAIR WELDING

Repair welding is limited to repairing local defects or indications. Repair welding is not allowed for major fabrication welding.

Weld repair shall be performed in accordance with the reconditioner's written procedures including the following as a minimum:



- Removal of the defect using a suitable means.
- Inspection of the excavated area using the same methods and criteria used to find the defect.
- Weld fill the subject area using qualified procedures and welders per 8.4.
- Grind or machine the welded surface to a finish and dimension(s) consistent with its purpose. As a minimum, surfaces shall be consistent with cleaned castings or forgings.
- Inspect the completed surface using the same methods and criteria used to find the defect.

## **8.6 NON-DESTRUCTIVE EXAMINATION (NDE)**

NDE, where applicable, shall be performed and evaluated by SNT-TC-1A or ISO 9712 Level II certified technicians. Procedures for the NDE evaluations shall be per ASME Section V, as a minimum.

## **9 Reassembly**

Valves shall be reassembled in accordance with documented procedures which are not less stringent than the OEM or owner's requirements and API Spec 6D. Special processes and procedures shall be provided in written instructions. New packing, gaskets, and non-metallic parts shall be used. See A.6 for replacement bolting requirements.

Interfaces between pressure controlling parts shall be assembled free of any sealant, except where the sealant is the primary means of sealing. A lubricant with a viscosity not exceeding that of SAE 10W motor oil or equivalent may be used if necessary for assembly of pressure controlling parts.

Other parts such as threads, bearings, sliding parts, etc. may be lubricated, if necessary for assembly, using an appropriate oil or grease.

Note: Valves specified by the owner as "critical service" valves for ethylene or other services shall not be lubricated during assembly. If minimal lubricant is required, the reconditioner shall supply details to the owner for evaluation.

## **10 Final Acceptance**

### **10.1 PRESSURE TESTING**

Repaired/remanufactured valves shall be pressure tested in accordance with the requirements of API Spec 6D, as a minimum. Supplemental tests may be performed as agreed between the owner and the reconditioner.

### **10.2 CUSTOMER NOTIFICATION**

Should the repaired or remanufactured valve not meet API or OEM requirements, the owner shall be notified by the reconditioner of such status.

## **11 Equipment Marking**

### **11.1 NAMEPLATES**

Nameplates shall be made from austenitic stainless steel or other material with equivalent or better corrosion resistance.

### **11.2 MARKING**

See Section 6 for additional marking information.

The following information shall be marked on an additional nameplate as indicated:

MARKING	LOCATION
Reconditioner's name or identifier	On nameplate
Date of repair or remanufacture	On nameplate
Nominal Valve Size	On nameplate
Pressure class designation	On nameplate
Pressure rating at 100°F (38°C)	On nameplate
Temperature rating	On nameplate
Body material designation (Material symbol such as ASTM, AISI, ISO, etc.)	On nameplate
Bonnet, cover plate, or tailpiece material designation (Material symbol such as ASTM, AISI, ISO, etc.)	On nameplate
Trim Identification (Symbols indicating the material of the stem and pressure controlling parts. MSS-SP-25 provides guidance for industry recognized symbols. The use of MSS-SP-25 symbols is recommended but not required)	On nameplate
Face to face or End to end dimension (Only if different from API Spec 6D)	On nameplate
Ring Joint Groove number (if not already marked on the valve)	End flange
Reconditioner's unique identification number	On nameplate and body

## 12 Preparation for Shipment and Short Term Storage

**12.1** All pressure shall be relieved and all test fluids shall be purged from the valve.

**12.2** Moving parts<sup>7</sup> shall be lubricated with a lubricant suitable to the design and function of the part, as applicable, only after successful completion of all pressure and functional testing.

Note: Valves specified by the owner as “critical service” valves for ethylene or other services shall not be lubricated during assembly. If minimal lubricant is required, the reconditioner shall supply details to the owner for evaluation.

**12.3** All non-corrosion resistant valves shall be externally primed/painted in accordance with the reconditioner's procedures or owner's procedures. Stainless steel valves shall not be painted unless specified otherwise by the owner. The seal surfaces of flange faces, weld bevel ends and exposed stems shall not be painted.

**12.4** Bare metal surfaces shall be protected with a rust preventative that provides protection at temperatures up to at least 50°C (122°F).

**12.5** Valves shall be prepared for shipment to prevent damage to internal and external components and allow for safe transport to the owner's designated location. Valve flanges and weld ends shall be blanked off to protect the gasket surfaces, weld preparations and valve internals during shipment and storage. Protective covers shall be made of suitable materials such as wood, wood fiber, plastic, or metal. They shall be securely attached to the valve by such means as bolting, steel straps, steel clips, or suitable friction locking devices. The design of the covers shall prevent the valve from being installed unless the covers are removed.

**12.6** Plug, ball, and gate valves shall be shipped in the fully open position, unless fitted with a “fail close” actuator. Check valves shall be shipped with the disc supported or secured during transit. Valves provided without an operating mechanism shall have significant annular spaces closed. Exposed stems shall be protected from damage.

## 13 Documentation

### 13.1 GENERAL DOCUMENTATION

Documentation shall be legible, retrievable, and reproducible. The following general documentation shall be maintained by the reconditioner:

- Weld Procedure Specifications (WPS)

<sup>7</sup>Bearings, operators, certain types of seat, etc.

- Weld Procedure Qualification Records (PQR)
- Welder Qualification Records (WQR)
- Qualification records of NDE Personnel
- Records of Test Equipment calibration
- Records of measuring equipment calibration

This documentation need not be traceable to a specific reconditioned valve unless agreed between the reconditioner and the owner.

### **13.2** Documentation for 2 in. (DN 50) and larger valves.

The following documentation shall be retained by the reconditioner for a minimum of five (5) years following the date of repair/remanufacture.

- Unique identification or serial number for tracing to the valve bill-of-material (BOM) or work order file
- Pressure test results
- Hardness tests, as applicable.

## APPENDIX A—MINIMUM REQUIREMENTS FOR EVALUATION AND RECONDITIONING OF PARTS

### A.1 Bodies, Bonnets, Closures, End pieces, Tailpieces and Covers

Body, bonnet, closures, end pieces, tailpiece, and covers shall be visually inspected. NDE may be employed to investigate the extent of visual defects. Injurious defects such as cracks or excessive metal loss shall be brought to the attention of the owner for disposition instructions (see Section 5).

Localized pitting or areas of localized corrosion that do not significantly affect the pressure retaining capability of the part are generally acceptable. Significant pitting or areas of metal loss corrosion that significantly affects the pressure retaining capability of the part shall be brought to the owner's attention for disposition instructions.

All tapped holes shall be visually inspected for missing or incomplete threads, defective thread profile, torn or ruptured surfaces and cracks. Defects shall be removed/repared using appropriate methods.

Visually inspect body to bonnet/tailpiece/cover flanges and seal surfaces for corrosion and overall condition. Body to bonnet gasket-sealing surfaces shall be visually inspected for corrosion, wear, cuts, or scoring. Dimensions and finish of the seal surface shall be per documented requirements not less stringent than the OEM or owner's requirements.

End connector dimensions shall comply with the applicable specification per API Spec 6D, paragraph 6.7. Face-to-face and end-to-end dimensions shall conform to API Spec 6D or to dimensions specified by the owner.

Stem seal preparations or stuffing boxes shall be examined for the proper condition and finish consistent with the seal design. Surface corrosion shall be removed by polishing, machining, or other suitable means. Dimensions and finishes of the reconditioned surface shall be consistent with the particular stem seal design being used and not less stringent than the OEM or owner's requirements.

### A.2 Stems

Stem sealing surfaces shall be smooth and free of defects that may affect the sealability or functionality of the part. The parts shall be free of burrs or other mechanical damage that may affect the strength, function, or fitness of the part for its intended use. The dimension of the sealing area shall be inspected and evaluated with respect to documented requirements that are not less stringent than the OEM or owner's requirements.

Threaded stems shall be inspected for missing or incomplete threads, defective thread profile, torn or ruptured surfaces and cracks. The surface texture of threaded parts may be evaluated without magnification.

Rising stems shall be inspected for straightness, finish, and cylindricity. Reconditioning may be by polishing, grinding, machining, welding, mechanical straightening, plating and grinding, or other suitable means.

Stem heads or other connections shall engage properly with the mating component.

### A.3 Pressure Controlling Parts (Gate, Ball, Plug, Disc, Seats, Clappers, etc.)

Pressure controlling parts shall be visually inspected for corrosion, wear, pitting, erosive wear, or other injurious defects. Defective parts shall be repaired, remanufactured, or replaced. Sealing surfaces shall have a profile (flatness, sphericity, etc.) consistent with the documented design requirements.

### A.4 Bearings

*Thrust Bearings*—Thrust bearings shall be free of damage, excessive corrosion, or wear. Operation shall be smooth.

*Sleeve Bearings*—Sleeve bearings shall be free of damage, excessive corrosion, or wear. Coatings or liners shall not be torn, damaged or excessively worn. Operation must be smooth.

Bearings not meeting the above requirements shall be replaced.

## **A.5 Stem Nut**

Visually inspect stem nut and stem housing for corrosion, galling or wear on the bearing surfaces. Internal and external threads shall be visually inspected for condition and proper engagement with the external stem threads. Defective parts shall be repaired by appropriate methods including, machining, welding, etc.

## **A.6 Body-to-Bonnet/Closure/End piece/Tailpiece/Cover Bolting**

Unless specified otherwise by the owner, all pressure containing bolting shall be replaced. Replacement bolting shall be in accordance with API Spec 6D.

Special or other bolting requirements are in accordance with the OEM design, owner's engineering piping requirements or as specified on the purchase order.

## **A.7 Other Components**

Other components shall be visually inspected and dispositioned based on documented requirements not less stringent than the OEM or owner's requirements. Disposition may include acceptance, remanufacture, or replacement.

Copyright American Petroleum Institute  
Provided by IHS under license with API  
No reproduction or networking permitted without license from IHS



## Bibliography

1. ISO/IEC Guide 22:1996, *General criteria for supplier's declaration of conformity*
2. ISO 9712, *Non-destructive testing—Qualification and certification of personnel*
3. EN 287-1, *Approval Testing of Welders—Fusion Welding—Part 1*
4. EN 288-3, *Specification and approval of welding procedures for metallic materials—Part 3: Welding procedure tests for the arc welding of steels*





American Petroleum Institute

# 2006 Publications Order Form

Effective January 1, 2006.

API Members receive a 30% discount where applicable.

The member discount does not apply to purchases made for the purpose of resale or for incorporation into commercial products, training courses, workshops, or other commercial enterprises.

Available through Global Engineering Documents:

Phone Orders: 1-800-854-7179 (Toll-free in the U.S. and Canada)  
303-397-7956 (Local and International)

Fax Orders: 303-397-2740

Online Orders: www.global.ihs.com

Date: \_\_\_\_\_

☐ API Member (Check if Yes)

Invoice To (☐ Check here if same as "Ship To")

Name: \_\_\_\_\_

Title: \_\_\_\_\_

Company: \_\_\_\_\_

Department: \_\_\_\_\_

Address: \_\_\_\_\_

City: \_\_\_\_\_ State/Province: \_\_\_\_\_

Zip/Postal Code: \_\_\_\_\_ Country: \_\_\_\_\_

Telephone: \_\_\_\_\_

Fax: \_\_\_\_\_

E-Mail: \_\_\_\_\_

Ship To (UPS will not deliver to a P.O. Box)

Name: \_\_\_\_\_

Title: \_\_\_\_\_

Company: \_\_\_\_\_

Department: \_\_\_\_\_

Address: \_\_\_\_\_

City: \_\_\_\_\_ State/Province: \_\_\_\_\_

Zip/Postal Code: \_\_\_\_\_ Country: \_\_\_\_\_

Telephone: \_\_\_\_\_

Fax: \_\_\_\_\_

E-Mail: \_\_\_\_\_

Quantity	Product Number	Title	SO★	Unit Price	Total
	GX06D22	Spec 6D, Specification for Pipeline Valves		\$104.00	
	CX60011	API Std 600, Bolted Bonnet Steel Gate Valves for Petroleum and Natural Gas Industries-Modified National Adoption		\$84.00	

☐ Payment Enclosed ☐ P.O. No. (Enclose Copy) \_\_\_\_\_

☐ Charge My Global Account No. \_\_\_\_\_

☐ VISA ☐ MasterCard ☐ American Express ☐ Diners Club ☐ Discover

Credit Card No.: \_\_\_\_\_

Print Name (As It Appears on Card): \_\_\_\_\_

Expiration Date: \_\_\_\_\_

Signature: \_\_\_\_\_

Subtotal

Applicable Sales Tax (see below)

Rush Shipping Fee (see below)

Shipping and Handling (see below)

Total (in U.S. Dollars)

★ To be placed on Standing Order for future editions of this publication, place a check mark in the SO column and sign here:

Pricing and availability subject to change without notice.

**Mail Orders** – Payment by check or money order in U.S. dollars is required except for established accounts. State and local taxes, \$10 processing fee\*, and 5% shipping must be added. Send mail orders to: **API Publications, Global Engineering Documents, 15 Inverness Way East, M/S C303B, Englewood, CO 80112-5776, USA.**

**Purchase Orders** – Purchase orders are accepted from established accounts. Invoice will include actual freight cost, a \$10 processing fee\*, plus state and local taxes.

**Telephone Orders** – If ordering by telephone, a \$10 processing fee\* and actual freight costs will be added to the order.

**Sales Tax** – All U.S. purchases must include applicable state and local sales tax. Customers claiming tax-exempt status must provide Global with a copy of their exemption certificate.

**Shipping (U.S. Orders)** – Orders shipped within the U.S. are sent via traceable means. Most orders are shipped the same day. Subscription updates are sent by First-Class Mail. Other options, including next-day service, air service, and fax transmission are available at additional cost. Call 1-800-854-7179 for more information.

**Shipping (International Orders)** – Standard international shipping is by air express courier service. Subscription updates are sent by World Mail. Normal delivery is 3-4 days from shipping date.

**Rush Shipping Fee** – Next Day Delivery orders charge is \$20 in addition to the carrier charges. Next Day Delivery orders must be placed by 2:00 p.m. MST to ensure overnight delivery.

**Returns** – All returns must be pre-approved by calling Global's Customer Service Department at 1-800-624-3974 for information and assistance. There may be a 15% restocking fee. Special order items, electronic documents, and age-dated materials are non-returnable.

**\*Minimum Order** – There is a \$50 minimum for all orders containing hardcopy documents. The \$50 minimum applies to the order subtotal including the \$10 processing fee, excluding any applicable taxes and freight charges. If the total cost of the documents on the order plus the \$10 processing fee is less than \$50, the processing fee will be increased to bring the order amount up to the \$50 minimum. This processing fee will be applied before any applicable deposit account, quantity or member discounts have been applied. There is no minimum for orders containing only electronically delivered documents.



# There's more where this came from.

The American Petroleum Institute provides additional resources and programs to the oil and natural gas industry which are based on API® Standards. For more information, contact:

- |   |  |
|---|--|
| • API Monogram® Licensing Program                         | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • American Petroleum Institute Quality Registrar (APIQR®) | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API Spec Q1® Registration                               | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API Perforator Design Registration                      | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API ISO/TS 29001 Registration                           | Phone: 202-962-4791<br>Fax: 202-682-8070 |
| • API Training Provider Certification Program             | Phone: 202-682-8490<br>Fax: 202-682-8070 |
| • Individual Certification Programs                       | Phone: 202-682-8064<br>Fax: 202-682-8348 |
| • Engine Oil Licensing and Certification System (EOLCS)   | Phone: 202-682-8516<br>Fax: 202-962-4739 |
| • API PetroTEAM™ (Training, Education and Meetings)       | Phone: 202-682-8195<br>Fax: 202-682-8222 |

Check out the API Publications, Programs, and Services Catalog online at [www.api.org](http://www.api.org).



American Petroleum Institute

Helping You Get  
The Job Done Right.®

Copyright American Petroleum Institute  
Provided by IHS under license with API  
No reproduction or networking permitted without license from IHS

Additional copies are available through Global Engineering Documents at (800) 854-7179 or (303) 397-7956

Information about API Publications, Programs and Services is available on the World Wide Web at: <http://www.api.org>



1220 L Street, Northwest  
Washington, D.C. 20005-4070

Product No. G06DR1